

Typ utwardzacza	ET	IDA	PAC	PAT	PF	Z-1	SADURAMID	T	TFF	IFF	IDA-2
				115 125 140			30-paź 10/50				
Epidian® 4	15		60-100	60-100	50-60	10		15	—		
Epidian® 5	18	50	60-100	60-100	50-60	12		18	26	50	*40
Epidian® 6	20	50	60-100	60-100	50-60	13		20	27	50	*40
Epidian® 61	15	*40	50-80	50-80	40-50	10		15	22	*40	
Epidian® 52	20	*50	60-100	60-100	50-60	13		20	27	*50	
Epidian® 53	15	*40	50-80	50-80	40-50	10		15	22	*40	
Epidian® 57	15	*40	50-80	50-80	40-50	10		15	22		
Epidian® 111	—		—	—	—	—	100	—	—		
Epidian® 112	—		—	—	—	—	90	—	—		
Epidian® 430	5		—	—	—	3		5	6		
Epidian® 450	14		50-80	50-80	40-50	9		14	20		
Epidian® 505	15		50-80	50-80	40-50	10		15	22		
Epidian® 561	10	25	—	—	—	—		10			
Epidian® 601	20	50	60-100	60-100	50-60	13		20	27	50	*40
Epidian® 607	20	50	60-100	60-100	50-60	13		20	27	50	*40
Epidian® 664											20
Epidian® 6011	18	*50	60-100	60-100	50-60	12		18	26	50	*40

* - brak badań mechanicznych